S 型异质结 CO₂ 还原光催化剂Swelm Wageh^{1,*}, Ahmed A. Al-Ghamdi¹, 刘丽君^{2,*}¹ Department of Physics, Faculty of Science, King Abdulaziz University, Jeddah 21589, Saudi Arabia.² 武汉纺织大学化学与化工学院, 武汉 430200S-Scheme Heterojunction Photocatalyst for CO₂ PhotoreductionSwelm Wageh^{1,*}, Ahmed A. Al-Ghamdi¹, Lijun Liu^{2,*}¹ Department of Physics, Faculty of Science, King Abdulaziz University, Jeddah 21589, Saudi Arabia.² College of Chemistry and Chemical Engineering, Wuhan Textile University, Wuhan 430200, China.

Emails: wswelm@kau.edu.sa (S.W.); liulj@wtu.edu.cn (L.L.)

Published online: October 19, 2020.

Photocatalytic CO₂ reduction to solar fuels attracts great interest due to the growing fossil fuel shortage and global warming. Developing high-efficiency photocatalyst is the key for the solar fuel production^{1,2}. TiO₂, as an inert, nontoxic and earth-abundant semiconductor, has been widely used for photocatalytic CO₂ reduction. Like other monocomponent photocatalysts, unitary TiO₂ shows poor photocatalytic activity because of its rapid electron/hole recombination. TiO₂-involved traditional type-II heterojunction is accepted to achieve efficient electron/hole separation³. However, as shown in Fig. 1a, the separated photogenerated electrons and holes will accumulate on the conduction band (CB) with less negative potential and the valence band (VB) with less positive potential, respectively. In general, less negative CB level and less positive VB level mean weaker photoreduction and photooxidation ability for the photogenerated electron and hole, respectively. From thermodynamic viewpoint, such charge transfer mechanism actually weakens the redox ability of the photogenerated

carriers, which is unfavorable for the photocatalytic reaction.

In 2019, Yu's group proposed the concept of S-scheme (Step-scheme) heterojunction to the dilemma that traditional type-II heterojunction confronts⁴. As shown in Fig. 1b, S-scheme heterojunction consists of two n-type semiconductors including reduction semiconductor (RS) and oxidation semiconductor (OS). RS has more negative CB potential, thus, stronger reduction ability for its photoexcited electrons. On the contrary, OS has more positive VB potential and stronger oxidation ability for its photoexcited holes. Usually, RS has higher Fermi level or smaller work function than OS. When such RS and OS semiconductors contact, their Fermi level difference drives electron transfer from RS to OS, resulting in RS and OS with the same Fermi level. Thus, the opposite charges are accumulated on their interface and form an internal electric field (IEF) pointing from RS to OS at the interfaces. Owing to the IEF and band bending, the useless photogenerated electrons on the CB of OS will transfer to RS and recombine with the useless holes on the

Fig. 1 Charge transfer routes in (a) traditional type-II heterojunction and (b) S-scheme heterojunction.

Fig. 2 Charge-transfer processes in $\text{TiO}_2/\text{CsPbBr}_3$ S-scheme heterojunction: (a) after contact, (b) IEF-induced charge transfer, separation, and the formation of S-scheme heterojunction under UV-visible light irradiation.

VB of RS. However, the useful photogenerated electrons and holes will retain on CB of RS and VB of OS, respectively. This results in the formed heterojunction with strong reduction and oxidation ability. Obviously, the transfer pathway of the photogenerated electron and hole in S-scheme heterojunction is completely different from that of traditional type-II heterojunction, which enables the photocarriers with strong redox capability⁵⁻⁸.

Very recently, Jiaguo Yu (Wuhan University of Technology), Jingsan Xu (Queensland University of Technology), Shengyao Wang (Huazhong Agricultural University) *et al.* reported an S-scheme heterojunction of $\text{TiO}_2/\text{CsPbBr}_3$ quantum dots (QDs) prepared by an electrostatic self-assembly method and used for photocatalytic CO_2 reduction (*Nature Communications* 2020, 11, 4613. doi: 10.1038/s41467-020-18350-7)⁹. In recent years, CsPbBr_3 QDs have attracted growing interest in photocatalysis owing to its narrow photoemission, visible light absorption, tunable band gap and effective CO_2 activation. TiO_2 and CsPbBr_3 are n-type semiconductors. The work function of TiO_2 is larger than that of CsPbBr_3 , implying that TiO_2 has a lower Fermi level than CsPbBr_3 before they contact. Upon hybridization, electrons flow from CsPbBr_3 to TiO_2 to enable them at the same Fermi level, which creates an IEF at $\text{TiO}_2/\text{CsPbBr}_3$ interfaces directing from CsPbBr_3 to TiO_2 and bends their energy bands (Figs. 1b and 2a). Under UV-visible light irradiation, as proved by *in situ* X-ray photoelectron spectroscopy (XPS) analysis, the photogenerated electrons in TiO_2 CB spontaneously transfer to CsPbBr_3 and recombine with the holes in CsPbBr_3 VB driven by the interfacial IEF and band bending. Finally, the electrons accumulating on CsPbBr_3 CB activate CO_2 molecules for photoreduction, and the holes aggregating on TiO_2 VB oxidize H_2O molecules to O_2 (Figs. 1b and 2b). Clearly, such transfer of photogenerated charge carriers causes the electron from TiO_2 CB to CsPbBr_3 CB, suggesting the formation of S-scheme heterojunctions between TiO_2 and CsPbBr_3 upon contact. This unique $\text{TiO}_2/\text{CsPbBr}_3$ S-scheme heterojunction greatly promotes the separation of electron-hole pairs and maintains their strong redox ability to foster efficient CO_2 photoreduction. The $\text{TiO}_2/\text{CsPbBr}_3$ hybrid nanofibers exhibit an enhanced CO production rate ($9.02 \mu\text{mol}\cdot\text{g}^{-1}\cdot\text{h}^{-1}$) with reference to TiO_2

nanofibers ($4.68 \mu\text{mol}\cdot\text{g}^{-1}\cdot\text{h}^{-1}$) under UV-visible light irradiation. This work provides new insights into TiO_2 -based photocatalysts for efficient CO_2 photoreduction driven by S-scheme charge separation.

Briefly, we highlight an emerging S-scheme heterojunction of $\text{TiO}_2/\text{CsPbBr}_3$ designed and fabricated by Xu *et al.* for efficient CO_2 photoreduction. This pioneering work offers great opportunity to deeply understand the S-scheme charge transfer and separation mechanism in the heterojunction. The novel concept along with its prospects would encourage collective efforts to develop more efficient S-scheme heterojunctions for solar-driven photocatalysis including water splitting, CO_2 reduction, and organic photosynthesis.

Acknowledgements: This project was funded by the Deanship of Scientific Research (DSR) at King Abdulaziz University, Jeddah (RG-50-130-41). The authors, therefore, acknowledge with thanks DSR for technical and financial support.

References

- (1) Shehzad, N.; Tahir, M.; Johari, K.; Murugesan, T.; Hussain, M. *J. CO₂ Util.* **2018**, 26, 98. doi: 10.1016/j.jcou.2018.04.026
- (2) Xiong, Z.; Lei, Z.; Li, Y.; Dong, L.; Zhao, Y.; Zhang, J. *J. Photochem. Photobiol. C* **2018**, 36, 24. doi: 10.1016/j.jphotochemrev.2018.07.002
- (3) Low, J.; Dai, B.; Tong, T.; Jiang, C.; Yu, J. *Adv. Mater.* **2019**, 30, 1802981. doi: 10.1002/adma.201802981
- (4) Fu, J.; Xu, Q.; Low, J.; Jiang, C.; Yu, J. *Appl. Catal. B* **2019**, 243, 556. doi: 10.1016/j.apcatb.2018.11.011
- (5) Xu, Q.; Zhang, L.; Cheng, B.; Fan, J.; Yu, J. *Chem* **2020**, 6, 1543. doi: 10.1016/j.chempr.2020.06.010
- (6) Xia, P.; Cao, S.; Zhu, B.; Liu, M.; Shi, M.; Yu, J.; Zhang, Y. *Angew. Chem. Int. Ed.* **2020**, 59, 5218. doi: 10.1002/anie.201916012
- (7) Ge, H.; Xu, F.; Cheng, B.; Yu, J.; Ho, W. *ChemCatChem* **2019**, 11, 6301. doi: 10.1002/cctc.201901486
- (8) He, F.; Zhu, B.; Cheng, B.; Yu, J.; Ho, W.; Macyk, W. *Appl. Catal. B* **2020**, 272, 119006. doi: 10.1016/j.apcatb.2020.119006
- (9) Xu, F.; Meng, K.; Cheng, B.; Wang, S.; Xu, J.; Yu, J. *Nat. Commun.* **2020**, 11, 4613. doi: 10.1038/s41467-020-18350-7